

**TABLE 2.6  
TEMPERATURE/PRESSURE RATINGS FOR  
FLANGES OF MALLEABLE IRON,  
AND DUCTILE IRON**

Flange	Pressure, kPa						Maximum allowable hydrostatic test pressure kPa
	Temperature °C						
Table	-18						
	to 120	150	175	190	200	220	
A	350	290	230	200	190	170	700