

**TABLE 2.9**  
**TEMPERATURE/PRESSURE RATINGS FOR**  
**FLANGES OF COPPER ALLOY DN 15**  
**TO DN 80 INCLUSIVE**

Flange  Table	Pressure, kPa							Maximum allowable hydrostatic test pressure kPa
	Temperature °C							
	-200 to 120	150	175	200	225	232	250	
A	350	170	170	170	170	170	...	525
D	700	650	650	570	500	450	400	1 050
E	1 400	1 400	1 400	1 200	1 000	900	750	2 100
F	2 100	2 100	2 100	1 800	1 400	1 350	1 200	3 150
H	3 500	3 500	3 500	2 900	2 400	2 300	1 900	5 250
J	3 800	3 600	3 600	3 100	2 800	2 700	2 500	5 700
K	4 800	4 600	4 600	4 000	3 600	3 500	3 200	7 200